

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
12 February 2004 (12.02.2004)

PCT

(10) International Publication Number
WO 2004/013061 A1

(51) International Patent Classification⁷: C03C 3/06, 4/00

(21) International Application Number:
PCT/EP2003/007914

(22) International Filing Date: 19 July 2003 (19.07.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2002-223673 31 July 2002 (31.07.2002) JP

(71) Applicants (for all designated States except US): HER-
AEUS QUARZGLAS GMBH & CO. KG [DE/DE];
Quartzstrasse 8, 63450 Hanau (DE). SHIN-ETSU
QUARTZ PRODUCTS CO., LTD. [JP/JP]; Shinjuku
San-Ei Bldg. 22-2, 1-chome Nishi-Shinjuku, Shinjuku-ku,
Tokyo 160-0023 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): FUJINOKI,

Akira [JP/JP]; 1-6-12, Midorigaoka-nishi, Koriyama-shi,
Fukushima 963-0701 (JP). NISHIMURA, Hiroyuki
[JP/JP]; 6-201-8, Kaisei, Koriyama-shi, Fukushima
963-8851 (JP). YOSHIDA, Kunio [JP/JP]; 18-8,
Kayashima-minami-machi, Neyagawa-shi, Osaka
572-0825 (JP).

(74) Agent: KÜHN, Hans-Christian; Heraeus Holding
GmbH, Patent Department, Heraeusstrasse 12-14, 63450
Hanau (DE).

(81) Designated State (national): US.


(84) Designated States (regional): European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: SYNTHETIC QUARTZ GLASS OPTICAL MATERIAL FOR YAG LASER WITH HIGHER HARMONIC



(57) Abstract: It is an object of the present invention to provide synthetic quartz glass optical materials suitable for use in YAG of higher order harmonics. The damage threshold value in J/cm² (energy density at which cracks occur generated by irradiation) is to be considered when synthetic quartz glass material is irradiated with YAG laser of third or higher order harmonics with single pulses or continuously. Regarding a synthetic quartz glass optical material in use for the optical parts constituting the prism and lens used in a laser beam machine, this invention provides a synthetic quartz glass material suitably used for the YAG laser with the third or higher order of harmonic, choosing the following conditions: OH group concentration is in the range of ≥ 1 to ≤ 300 ppm;

contained hydrogen molecule concentration is in the range of $\geq 2 \times 10^{18}$ to $\geq 2 \times 10^{19}$ molecules/cm³; transmittance of ultraviolet rays at 245nm of wavelength is 99.9% or more; and the fictive temperature is in the range of ≥ 880 to $\leq 990^\circ\text{C}$.

WO 2004/013061 A1